

Technical Data Sheet (TDS)

Hyper Speed Dual Color Silk PLA

Eryone Hyper Speed Dual Color Silk PLA filament extrudes two colors simultaneously, resulting in vibrant and varied colors visible on different surfaces with smooth color transitions. Utilizing a comprehensively improved formula, it offers significantly faster printing speeds compared to standard silky PLA, reaching up to 500 mm/s. Furthermore, its tensile strength is greatly enhanced, with a Z-axis tensile strength approaching 20 MPa. This high-speed silky PLA material delivers a brighter surface with a silky sheen. Brightness can be controlled by adjusting temperature and speed: higher temperatures and lower printing speeds result in higher brightness.

Part I: Suggests Printing Parameters

| Parameter | Set up |
|-----------------------------|--------------------------------|
| Nozzle temperature | 190°C-220°C |
| Bed temperature | 55-70°C |
| Bed material | glass, PEI, spring steel plate |
| Bottom printing temperature | 190°C-220°C |
| Sealed printing | Open Printing/closed printing |
| Printing speed | 30-500mm/s |
| Drying conditions | 50°C-60°C , 6h |

Part II: Physical Properties of Materials

| Property | Testing Method | Unit | Typical Value |
|--|---------------------------------|-------------------|---------------|
| Density(g/cm ³ at 21.5 ° C) | ASTM D792 (ISO 1183, GB/T 1033) | g/cm ³ | 1.32 |
| Vicat Softening Temperature(° C) | ASTM D1525 (ISO 306 GB/T 1633) | °C | 56 |
| Heat distortion temperature(° C) | ASTM D648 0.45MPa | °C | 50 |
| Glass transition temperature (° C) | DSC, 10 ° C/min | °C | 57 |
| Melt Index(g/10 min) | 220 ° C, 10kg 240 ° C, 2.16 kg | g/10min | 20±1.5 |


Part III: Mechanical Properties of Printed Samples

| Property | Test conditions | Test standards | unit | Typical Value |
|-------------------------|-----------------|------------------|-------|---------------|
| Tensile strength X-Y | 50mm/min | GB/T 1040.4 | MPa | 62.7 |
| Elastic modulus X-Y | 50mm/min | GB/T 1040.1-2006 | MPa | 1932.1 |
| Elongation at break X-Y | 50mm/min | GB/T 1040.4 | % | 2.3 |
| Tensile strength X-Z | 50mm/min | GB/T 1843 | MPa | 19.1 |
| Elastic modulus X-Z | 50mm/min | GB/T 1040.1-2006 | MPa | 1873.5 |
| Elongation at break X-Z | 50mm/min | GB/T 1040.4 | % | 1.9 |
| Bending strength | 2mm/min | GB/T 9341 | MPa | 86.7 |
| Bending modulus | 2mm/min | GB/T 9341 | MPa | 2917.3 |
| Charpy Impact strenght | 2.75J | GB/T 1843 | kJ/m2 | 3.8 |

Note: All splines are printed under the following conditions: printing temperature=215 ° C, printing speed=80mm/s, base plate 60 ° C, filling=100%, nozzle diameter=0.4mm


TENSILE TESTING SPECIMEN

ISO 527,GB/T 1040




FLEXURAL TESTING SPECIMEN

ISO 178,GB/T 9341



IMPACT TESTING SPECIMEN

ISO 179,GB/T 1043



Disclaimers

The values given in this data table are for reference and comparison only. They should not be used for design specifications or quality control. The actual value may vary depending on the printing conditions. The final performance of printed components depends not only on the material, but also on the component design, environmental conditions, printing conditions, and so on. Product specifications are subject to change without prior notice.